



Unit E, 3 Tudor Road, Altrincham Business Park, Cheshire, WA14 5RZ
Tel : 0161 975 9002 Email : sales@friedmans.co.uk Web : www.friedmans.co.uk

Technical Data Sheet

Article	Alicante Net	
Composition	80% POLYAMIDE 20% ELASTANE	
Weight m ² (+/- 5%)	65 g/m²	
Weight linear m. (+/- 5%)	99 g/m lin.	
Total width (+/- 2%)	152 cm	
Dimensional Stability – Washing 40° C - flat dry BS EN ISO 6330	width -5% MAX	length -5% MAX
Dimensional Stability – Steam	width -4% MAX	length -4% MAX
Resistance to pilling NU Martindale – ISO 12945-2 7000 rotations	on fabric 4/5	on wool 4/5
Hand Elongation (+/- 15%)	width 120% (min 102% - max 138%)	length 200% (min 170% - max 230%)
Stretch to Dynamometer (+/- 15%) INSTRON 3343 – 3.6 kg strip test - size of the tested sample: 100 mm x 50 mm		
Plain dyed	width 115% (min 98% - max 132%)	length 195% (min 166% - max 224%)
<i>Modulus 40%</i> Plain dyed	width 95-175g	length 65-125g
Ultraviolet Protection Factor (ref. standard AS/NZS 4399:2017)	5	

Care labelling codes:



Feather weight



Perfect Fit



Ultra Flat



4 Way Stretch

Notes:

Technical Specification details prior to a print or foil application.

Please note due to the numerous different Industries we supply, we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests

We recommend testing each dyebath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.