



Unit E, 3 Tudor Road, Altrincham Business Park, Cheshire, WA14 5RZ  
 Tel : 0161 975 9002 Email : sales@friedmans.co.uk Web : www.friedmans.co.uk

Technical Data Sheet

Article	<b>Crushed Velvet</b>	
Composition	<b>85% POLYAMIDE 15% ELASTANE</b>	
Weight m <sup>2</sup> (+/- 5%)	<b>210 g/m<sup>2</sup></b>	
Weight linear m. (+/- 5%)	<b>294 g/m lin.</b>	
Total width (+/- 2%)	<b>140 cm</b>	
Dimensional Stability – Washing 40° C BS EN ISO 6330 – flat dry	width <b>-6% MAX</b>	length <b>-6% MAX</b>
Dimensional Stability – Steam	width <b>-4% MAX</b>	length <b>-6% MAX</b>
Resistance to pilling NU Martindale – ISO 12945-2 7000 rotations	on fabric <b>4/5</b>	on wool <b>3/4</b>
Hand Elongation (+/- 15%)	width <b>150%</b> (min 127% - max 172%)	length <b>220%</b> (min 187% - max 253%)
Stretch to Dynamometer (+/- 15%) INSTRON 3343 – 3.6 kg - strip test - size of the tested sample: 100 mm x 50 mm	width <b>140%</b> (min 119% - max 161%)	length <b>210%</b> (min 178% - max 241%)
<i>Modulus 40%</i>	width <b>60-140g</b>	length <b>60-140g</b>

Care labelling codes:



Velvet



Soft



Perfect Fit



Excellent Coverage



UV Protection



Pilling Resistant



4 Way Stretch



Resistance to Sun Cream / Oil

Notes:

Technical Specification details prior to a print or foil application.

Please note due to the numerous different Industries we supply, we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests

We recommend testing each dye bath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.