



Unit E, 3 Tudor Road, Altrincham Business Park, Cheshire, WA14 5RZ
Tel : 0161 975 9002 Email : sales@friedmans.co.uk Web : www.friedmans.co.uk

Technical Data Sheet

Article	lbiza	
Composition	93% POLYAMIDE 7% ELASTANE	
Weight m ² (+/- 10%)	270 g/m²	
Weight linear m. (+/- 10%)	311 g/m lin.	
Total width (+/- 4%)	115 cm	
Dimensional Stability – Washing 40° C BS EN ISO 6330 – flat dry	width -6% MAX	length -6% MAX
Dimensional Stability – Steam	width -4% MAX	length -4% MAX
Resistance to pilling NU Martindale – ISO 12945-2 7000 rotations	on fabric 4/5	on wool 4
Hand Elongation (+/- 15%)	width 165% (min 140% - max 190%)	length 325% (min 276% - max 374%)
Stretch to Dynamometer (+/- 15%) INSTRON 3343 – load 3.6 kg - strip test - size of the tested sample: 100 mm x 50 mm.		
Plain dyed	width 160% (min 136% - max 184%)	length 320% (min 272% - max 368%)
<i>Modulus 40%</i>	width 10-80g	length 10-80g

Care labelling codes:



Two-way
Stretch



Pilling
Resistant

Notes:

Please note due to the numerous different Industries we supply, we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests.

We recommend testing each dyebath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.