



Unit E, 3 Tudor Road, Altrincham Business Park, Cheshire, WA14 5RZ
Tel : 0161 975 9002 Email : sales@friedmans.co.uk Web : www.friedmans.co.uk

Technical Data Sheet

Article

LP Life Recycled Polyester

Composition

**78% POLYESTER
22% ELASTANE**

Weight m² (+/- 5%)

190 g/m²

Weight linear m. (+/- 5%)

285 g/m lin.

Total width (+/- 2%)

150 cm

Dimensional Stability – Washing 40° C

width **-5% MAX**

BS EN ISO 6330 – flat dry

length **-5% MAX**

Dimensional Stability – Steam

width **-3% MAX**

length **-3% MAX**

Resistance to pilling

on fabric **5**

on wool **4/5**

NU Martindale – ISO 12945-2 7000 rotations

Hand Elongation (+/- 15%)

width **95%**

(min 81% - max 109%)

length **135%**

(min 115% - max 155%)

Stretch to Dynamometer (+/- 15%)

INSTRON 3343 – load 3.6 kg - strip test - size of the tested sample: 100 mm x 50 mm

Plain Dyed

width **90%**

(min 77% - max 104%)

length **130%**

(min 111% - max 150%)

Modulus 40%

Plain Dyed

width **210-390g**

length **170-310g**

Care labelling codes:



Recycled
Polyamide



Ultra Chlorine
Resistant



Sun Creams and
Oil Resistant



Muscle
Control



Shape
Retention



Excellent UV
Protection



Excellent
Coverage



Ultra Flat



Soft



Two-way
Stretch



Pilling Resistant

Notes:

Technical Specification details prior to a print or foil application.

Please note due to the numerous different Industries we supply; we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests.

We recommend testing each dyebath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.