



Unit E, 3 Tudor Road, Altrincham Business Park, Altrincham, Cheshire, WA14 5RZ, UK  
 Tel : 0161 975 9002 Fax : 0161 975 9003 email : [sales@friedmans.co.uk](mailto:sales@friedmans.co.uk)

### Technical Data Sheet

Article	<b>Perform</b>	
Composition	<b>80% POLYAMIDE 20% ELASTANE</b>	
Weight m <sup>2</sup> (+/- 5%)	<b>225 g/m<sup>2</sup></b>	
Weight linear m. (+/- 5%)	<b>337 g/m lin.</b>	
Total width (+/- 2%)	<b>150 cm</b>	
Dimensional Stability – Washing 40° C BS EN ISO 6330 – flat dry	width <b>-4% MAX</b>	length <b>-4% MAX</b>
Dimensional Stability – Steam	width <b>-3% MAX</b>	length <b>-3% MAX</b>
Resistance to pilling NU Martindale – ISO 12945-2 7000 rotations	on fabric <b>5</b>	on wool <b>5</b>
Hand Elongation (+/- 15%)	width <b>110%</b> (min 94% - max 127%)	length <b>170%</b> (min 145% - max 196%)
Stretch to Dynamometer (+/- 15%) INSTRON 3343 – 3.6 kg - strip test - size of the tested sample: 100 mm x 50 mm. Plain Dyed	width <b>105%</b> (min 89% - max 121%)	length <b>165%</b> (min 140% - max 190%)
<i>Modulus 40%</i>	width <b>175-325g</b>	length <b>120-220g</b>

Care labelling codes:



Muscle Control



Pilling Resistant



Shape Retention



UV Protection



Perfect Fit



Excellent Coverage



4 Way stretch



Ultra chlorine resistant

Notes:

Technical Specification details prior to a print or foil application.

Please note due to the numerous different Industries we supply, we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests

We recommend testing each dye bath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.