



Unit E, 3 Tudor Road, Altrincham Business Park, Cheshire, WA14 5RZ
Tel : 0161 975 9002 Email : sales@friedmans.co.uk Web : www.friedmans.co.uk

Technical Data Sheet

Article	Renew Soul	
Composition	84% POLYAMIDE (recycled) 16% ELASTANE	
Weight m ² (+/- 5%)	80 g/m²	
Weight linear m. (+/- 5%)	120 g/m lin.	
Total width (+/- 2%)	150 cm	
Dimensional Stability – Washing 40° C BS EN ISO 6330 - @40°C - flat dry	width -5% MAX	length -5% MAX
– Steam	width -3% MAX	length -3% MAX
Resistance to pilling NU Martindale – ISO 12945-2 7000 rotations	on fabric 2/3	on wool 2
Stretch to Dynamometer (+/- 15%) ZWICK – load 1,5 KG - strip test – size of the tested sample: 100mm x 50mm	width 200% (min 170% - max 230%)	length 180% (min 153% - max 207%)
Modulus 40%	width 35-65g	length 20-50g

Care labelling codes:



RECYCLED
YARN



TWO WAY STRETCH



QUICK DRYING



SOFT

Notes:

Technical Specification details prior to a print or foil application.

Please note due to the numerous different Industries we supply, we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests

We recommend testing each dyebath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.