



Unit E, 3 Tudor Road, Altrincham Business Park, Cheshire, WA14 5RZ  
 Tel : 0161 975 9002 Email : sales@friedmans.co.uk Web : [www.friedmans.co.uk](http://www.friedmans.co.uk)

### Technical Data Sheet

Article	<b>Riviera</b>	
Composition	<b>80% POLYAMIDE 20% ELASTANE</b>	
Weight m <sup>2</sup> (+/- 5%)	<b>210 g/m<sup>2</sup></b>	
Weight linear m. (+/- 5%)	<b>315 g/m lin.</b>	
Total width (+/- 2%)	<b>150 cm</b>	
Dimensional Stability – Washing 40° C BS EN ISO 6330	width <b>-5% MAX</b>	length <b>-5% MAX</b>
Dimensional Stability – Steam	width <b>-4% MAX</b>	length <b>-4% MAX</b>
Resistance to pilling NU Martindale – ISO 12945-2 7000 rotations	on fabric <b>4/5</b>	on wool <b>4</b>
Hand Elongation (+/- 15%)	width <b>160%</b> (min 136% - max 184%)	length <b>240%</b> (min 204% - max 276%)
Stretch to Dynamometer (+/- 15%) INSTRON 3343 – load 3.6 kg - strip test - size of the tested sample: 100 mm x 50 mm.		
Plain dyed	width <b>150%</b> (min 127% - max 172%)	length <b>230%</b> (min 195% - max 264%)
<i>Modulus 40%</i>		
Plain dyed	width <b>75-125g</b>	length <b>65-115g</b>

Care labelling codes:



Perfect Fit



Ultra Chlorine Resistant



Sun Creams and Oil Resistant



Shape Retention



Two-way Stretch



Excellent UV Protection



Soft

#### Notes:

Technical Specification details prior to a print or foil application.

Please note due to the numerous different Industries we supply, we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests.

We recommend testing each dyebath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.